

PCT


WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B41M 3/14, 5/38, G06K 7/12, B42D 15/10, G07D 7/00		A1	(11) International Publication Number: WO 97/32733
			(43) International Publication Date: 12 September 1997 (12.09.97)
(21) International Application Number: PCT/US97/03556		(81) Designated States: AU, CA, CN, IL, JP, KR, MX, SG, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 7 March 1997 (07.03.97)			
(30) Priority Data: 60/012,997 7 March 1996 (07.03.96) US 08/811,311 4 March 1997 (04.03.97) US		Published With international search report.	
(71) Applicant: EASTMAN CHEMICAL COMPANY [US/US]; 100 North Eastman Road, Kingsport, TN 37660 (US).			
(72) Inventors: KRUTAK, James, John, Sr.; 6305 Booth Court, Kingsport, TN 37663 (US). CYR, Michael, John; 204 Coralwood Drive, Kingsport, TN 37663 (US). ESCANO, Nelson, Zamora; 304 Appleberry Circle, Kingsport, TN 37663 (US). CLAUBERG, Horst; 2601 John B. Dennis Highway #210, Kingsport, TN 37660 (US). JACKSON, Barbara, Crawford; 404 Arbutus Avenue, Kingsport, TN 37660 (US). HELTON, Tony, Wayne; 424 Light Street, Kingsport, TN 37663 (US).			
(74) Agent: HARDING, Karen, A.; P.O. Box 511, Kingsport, TN 37662-5075 (US).			

(54) Title: NEAR INFRARED FLUORESCENT SECURITY THERMAL TRANSFER PRINTING AND MARKING RIBBONS



(57) Abstract

The present invention relates to thermal transfer ribbons comprising a ribbon backing element and at least one printing media layer comprising at least one near infrared fluorescent compound in a concentration which provides detectable fluorescence without imparting color to a mark made from said printing media layer. Methods for printing marks containing said at least one near infrared fluorescent compound via thermal transfer and methods for reading said marks are also disclosed.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

5 **NEAR INFRARED FLUORESCENT SECURITY THERMAL TRANSFER
PRINTING AND MARKING RIBBONS**

Field of the Invention

10 This invention relates to thermal transfer printing media containing near-infrared fluorophores (NIRFS) which may be monomeric, copolymerized or admixed into a carrier polymer/polymer backbone which is incorporated into the wax/thermoplastic resin which forms the thermally meltable ink layer (or printing media layer) on the thermal transfer ribbon.

15 **Background of the Invention**

 Thermal transfer printing media and the ribbons used for thermal transfer are well known in the art. Generally the ribbon comprises at least three main layers, a thermally meltable ink layer, a polymer film layer and a heat resistant polymer layer. The compositions of the various layers are described in JP A 3-79,683, (April 4, 1991).
20 However, thermal transfer media or ribbons capable of printing invisible marks are not disclosed.

 Thermal transfer ribbons incorporating visible fluorescent dyes or pigments are disclosed in U.S. Patent No. 4,627,997, 4,657,697, 4,816,344, 5,089,350 and 5,552,231. Ribbons containing marking compositions, which are invisible to the human eye, are not
25 disclosed.

 Thermal transfer ribbons incorporating invisible UV dyes or pigments and visible pigments are disclosed in U.S. Patent No. 5,516,590. However, thermal transfer ribbons incorporating invisible marking compound which are not visible to the unaided human eye, and particularly invisible near infrared fluorescent compounds are not disclosed.

30

Summary of the Invention

 The present invention relates to thermal transfer ribbons comprising a ribbon backing element and at least one printing media layer comprising at least one near infrared fluorescent compound in a concentration which provides detectable
35 fluorescence without imparting color to a mark made from said printing media layer.

 The present invention further relates to preparation of printing and marking ribbons consisting of thin film elements with printing media adhered to one side thereof.

5 Also disclosed is a method for applying a mark comprising at least one invisible near infrared fluorescent compound said method comprising the steps of providing a thermal transfer ribbon comprising a ribbon backing element having coated on one side at least one printing media layer comprising at least one invisible NIRF compound; and contacting the non-coated side of said ribbon backing element with a heating element so as
10 to contact said printing media layer with a print receiving media under conditions sufficient to thermally transfer an image to said print receiving media.

 Also disclosed is a method for detecting a thermal transfer mark comprising at least one invisible NIRF compound wherein said method comprises the steps of exciting said at least one invisible NIRF compound having a peak absorbance with radiation
15 focused within 10 nm of said peak absorbance; and detecting fluorescence emitted from said invisible NIRF compound.

Description of the Figures

20 **Figure 1** is a cross-sectional side view of a thermal transfer ribbon having a single printing media layer containing both visible and invisible NIRF marking compounds.

Figure 2 is a cross-sectional side view of a thermal transfer ribbon comprising a single printing media layer containing at least one invisible NIRF marking compound.

Figure 3 is a cross-sectional side view of a thermal transfer printing ribbon having
25 a first media layer containing at least one visible marking compound, and a second media layer containing at least one invisible NIRF marking compound.

Figure 4 is a cross-sectional side view of a thermal transfer printing ribbon having a first media layer containing at least one invisible NIRF marking compound which is applied to said ribbon in a predetermined configuration and a second media layer
30 containing at least one visible marking compound.

Figure 5 is a top view of the thermal transfer printing ribbon shown in **Figure 4**.

Figure 6 is a top view of a thermally transferred bar code as printed on a print receiving medium using the ribbon shown in **FIG. 1** or **FIG. 3** or **FIG. 4**, as the bar code would visibly appear under broad spectrum light or black light.

35 **Figure 6A** is a top view of a thermally transferred bar code printed on a print receiving medium using the ribbon shown in **Fig 2** as the product identification bar code would appear under broad spectrum and/or black light.

5 Figure 6B is a top view of the bar code in Figure 6A as the bar code would appear when excited with an appropriate near infrared radiation source and imaged with a camera designed to display contrast images of the fluorescence.

 Figure 7 is a top view of a thermally transferred bar code as printed on a print receiving medium using the ribbon shown in FIG. 4, as the bar code would appear when
10 excited with an appropriate near infrared radiation source and imaged with a camera designed to display contrast images of the fluorescence .

 Figure 8 is a cross-sectional side view of a thermal transfer ribbon having a first media layer containing at least one visible marking compound, a second media layer containing at least one invisible NIRF marking compound which is applied to said ribbon
15 in a predetermined configuration and a third media layer containing at least one second invisible marking compound which is applied to said ribbon in a second predetermined configuration.

 Figure 9 is a top view of the ribbon shown in FIG 8.

 Figure 10 is a top view of a bar code as printed on a print receiving medium using
20 the ribbon of FIG. 8, as the bar code would appear under broad spectrum or black light.

 Figure 11 is a top view of the bar code shown in Figure 10 as it would appear when excited with an appropriate near infrared radiation source and imaged with a camera designed to display contrast images of the fluorescence.

 Figure 12 is a diagram of the components of an apparatus suitable for scanning
25 and imaging the near infrared fluorescent marks of the present invention.

Detailed Description of the Invention

 The thermal transfer ribbons 10 of the present invention comprise at least three main layers: at least one thermally meltable ink or printing media layer 12 containing at
30 least one NIRF compound which is adherent to one side of a polymer film layer or ribbon backing element 14 and a heat resistant polymer layer. Ribbon backing element 14 is preferably a long narrow strip of a flexible polymeric material. The ribbon backing should be compatible with printing media layer 12, have sufficient tensile strength to resist tearing and be sufficiently flexible to be wound around a spool or reel. Suitable backing materials
35 include tissue paper, PET, PEN, a copolymer or blend of PET and/or PEN and Mylar. Preferably said backing material is Mylar, such as that available from E. I. Dupont de Nemours and Co., Inc. in Wilmington, Del.

 The printing media 12 of the present invention comprises a binding substrate and at least one marking compound selected from visible marking compounds such as

5 pigments and dyes 16 and invisible NIRF marking compounds such as copolymerized NIRF compounds and monomeric NIRF compounds 18. Thus, the term marking compound as used herein includes both visible pigments and dyes as well as copolymerized and monomeric NIRF compounds, which are invisible to the human eye.


10 Thermal transfer ribbons according to the present invention may include more than one printing media layer, however, at least one printing media layer must include at least one invisible NIRF compound either alone or in combination with other invisible NIRF compounds or visible marking compounds. Preferably said printing media is a uniform dispersion.

Binding substrate 20 retains the uniform dispersion of marking compounds 16 and 18 against the ribbon-backing element 14 prior to the printing operation. In addition, binding substrate 20 retains the uniform dispersion of marking compounds 16 and 18 once printing media layer 12 is transferred onto print receiving medium. Suitable binding substrates contain carnuba wax, paraffin wax, candelilla wax, palm wax, beeswax and other natural waxes or oils such as rice bran wax, gum arabic, wax compatible resins and 20 chemicals such as poly(α -methyl styrene), epoxy resins, acrylic resins, polyethylene oxide, polytetrafluoroethylene wax, polyurethanes, polyethylene waxes, methyl methacrylate resins, styrene-ethylene-butylene block copolymers, ethylene vinyl acetate, ethylene methyl acrylate copolymers, styrene butadiene elastomers, polyketones, amorphous polyester resins, cellulose esters, polyvinyl alcohol, solid fatty acids, amides and alcohols 25 such as 1-octadecanol, sebacic acid, stearamide, behenyl alcohol, stearyl stearamide, casein, high density polyethylene emulsion, carnuba wax emulsion, glycerine, castor oil, plasticizers, curing agents such as glycidoxypolydimethoxy silane, n-beta-amino ethyl gammaaminopropyl ethylenediamine, defoamers such as NopcoNDW and surfynol 104.

Visible marking compounds allow the printed image to appear visibly black or 30 colored, as desired, under broad spectrum light. Visible marking compounds include visible pigments, dyes and other colorants which are known in the art and which can be suitably dispersed in the printing media. Examples of suitable visible marking compounds 16 include carbon black pigments, green, brown, blue and other colored pigments in concentrations sufficient to impart color to the print receiving media.


35 Invisible NIRF marking compounds are invisible under broad spectrum light and black light but produce fluorescence or fluoresce when activated with appropriate infrared light frequencies. Suitable invisible marking compounds include monomeric or copolymerized near infrared fluorescent compounds or NIRFs.

- 5 The NIRF dyes useful in the practice of the present invention and for the synthesis of NIRF polymers useful in the practice of the present invention comprise at least one porphine composition described by the formula:



10





- wherein each X may be the same or different and is selected from nitrogen and carbon substituted with Y, wherein Y is selected from hydrogen, C₁-C₁₂ alkyl, substituted C₁-C₁₂ alkyl, C₃-C₈ cycloalkyl, aryl and heteroaryl, m is 1 through 9; R₁ - R₈ are the same or different and are selected from hydrogen, C₁-C₁₂ alkyl, substituted C₁-C₁₂ alkyl, C₃-C₈ cycloalkyl, aryl and heteroaryl and wherein adjacent R₁-R₈ groups may represent the following parts of aromatic and heteroaromatic ring systems:
- 15




- wherein X_1 and X_2 may be the same or different and are O, N or S; TH
 5 wherein A is 2(H) atoms bonded to diagonally opposite nitrogen atoms or Zn(II), Mg(II),
 Al (III) bonded to halogen, oxygen, sulfur or nitrogen, Sn(IV) atoms bonded to halogen,
 oxygen, sulfur or nitrogen, Si(IV) bonded to halogen, oxygen, sulfur or nitrogen and Ga(III)
 bonded to halogen, oxygen, sulfur or nitrogen and any other metal for S which produces
 near infrared fluorescence such as Li, Na, K, Be, Mg, Ca, Sc, Y, La, Ac, Ti, Zr, Hf, Cr,
 10 Mo, W, Mn, Tc, Re, Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, Pt, Cu, Ag, Au, Zn, Cd, Hg, In, Tl, Ge,
 Pb, As, Sb; lanthanides: Pr, Nd, Sm, Eu, Gd, Dy, Ho, Er, Tm, Yb, Lu; and actinides: Th,
 Pa U Np. S represents 1-8 substituents bearing polymer forming reactive groups (capable
 of producing a polymer) which may be substituted into Y or the R_1 - R_8 groups or both.

- In the case of the R_1 - R_8 groups and Y, any nuclear position can be used which
 15 produces the desired light absorption and fluorescence properties. The scope of the R_1 - R_8
 includes symmetric and less symmetric combination of ring systems designed to increase
 the absorption wavelengths. By designing the NIRFs with higher absorption wavelengths
 the color of the resultant compound is minimized.

- Preferably X is 0, 2 or 4 nitrogens, more preferably 2 (diazaporphines) or 4
 20 nitrogens (tetra azaporphines) and most preferably 4 nitrogens. Example of suitable tetra
 azaporphines includes, but are not limited to:



5



wherein each Ar, Ar₁-Ar₈ group is independently selected from fused aryl ring systems having one to four aryl rings fused therein and preferably from 1 to three rings. Preferably the Ar, Ar₁^r-Ar₈^r groups are oriented symmetrically about the pyrrole nuclei. For example,

msc TH
76 GK
57 P.

- 5 if m is an even number the $Ar, Ar_1^1-Ar_2^2$ groups may be opposite from each other or alternating in structures where m is more than 3. If m is even the $Ar, Ar_1^1-Ar_2^2$ groups may be disposed in any configuration, which provides the desired degree of symmetry. Preferably the "symmetric" $Ar, Ar_1^1-Ar_2^2$ groups have the same number of fused aryl rings therein. Moreover, for greatest ease of synthesis, all $Ar, Ar_1^1-Ar_2^2$ groups in a NIRF are the same. Preferably, A in the above general structure represents Al and Si bonded to halogen or oxygen or sulfur or nitrogen. Other suitable NIRFs are disclosed in U.S. 5,397,819 and 5,416,136, which are incorporated herein by reference.
- 10

TH MR
KL JK
BG
GR

- As described above, S is or contains the polymer forming reactive group, which provides the NIRF with its copolymerizability or reactivity to the polymer backbone.
- 15 Suitable reactive groups vary depending upon the backbone polymer, which is selected. Examples of such (S) groups include, but are not limited to:

O-arylene $\text{CH}=\text{CH}_2$, O- $\text{C}_1\text{-C}_{12}$ alkylene arylene- $\text{CH}=\text{CH}_2$, O- $\text{CH}_2\text{CH}=\text{CH}_2$,


$$\text{O-C}_1\text{-C}_{12}\text{ alkylene-CO}_2\text{CH=CH}_2, \text{O-C}_1\text{-C}_{12}\text{ alkylene-CO}_2\underset{\text{CH}_3}{\text{C=CH}_2}, \text{OC}_1\text{-C}_{12}\text{ alkylene-OC}\overset{\text{O}}{\underset{\text{CH}_3}{\text{C=CH}_2}},$$
$$\text{C}_1\text{-C}_{12} \text{ alkylenearylene}-\text{CH}=\text{CH}_2, \text{NH-arylene-C}_1\text{-C}_{12} \text{ alkylene-CO}_2\text{CH}=\text{CH}_2, \text{OCC(=O)-C}_1\text{-C}_{12} \text{ alkyl},$$
$$\text{NHCCH=CH}_2, \text{C}_1\text{-C}_{12} \text{ alkylene-NHCCH=CH}_2, \text{NH arylene NHCOCH=CH}_2,$$

Z-C₁-C₁₂ alkylene-I, Z-arylene-CHO, Z-CH₂ CH=CH₂, Z-arylene CH=CH₂

$$\text{-NH}_2, \text{Z-arylene-NH}_2, \text{Z-C}_1\text{-C}_{12} \text{ alkylene-NH}_2, \begin{array}{c} \text{O} \\ || \\ \text{OCC-CH}_2 \\ | \\ \text{CH}_3 \end{array}, \begin{array}{c} \text{O} \\ || \\ \text{OCCH=CH}_2 \end{array}, \begin{array}{c} \text{O} \\ | \\ \text{CH}_2\text{CH-CH}_2 \\ | \\ \text{O} \end{array}$$

Z-arylene-CO₂-, C₁-C₁₂ alkylene-, CO₂-C₁-C₁₂ alkylene-, NHC₁-C₁₂ alkyl,

Z-arylene-SO₂-CH=CH₂, C₁-C₁₂ alkylene-SO₂-CH=CH₂, C₁-C₁₂ alkylene-Z-CH=CH₂,


$$-\text{SO}_2\text{CH}=\text{CH}_2, \text{Z-C}_1\text{-C}_{12} \text{ alkylene-SO}_2\text{CH}=\text{CH}_2, \text{Z-arylene-Z-CH}_2\underset{\text{O}}{\underset{\text{O}}{\text{CH}}}\text{CH}_2,$$
$$\text{Z-C}_1\text{-C}_{12}\text{ alkylene-OH, Z-C}_1\text{-C}_{12}\text{ alkylene-O-C(=O)-C}_1\text{-C}_{12}\text{ alkyl, OH, C}_1\text{-C}_{12}\text{ alkylene-OH,}$$

C₁-C₁₂ alkylene-CO₂H, C₁-C₁₂ alkylene-CO₂-C₁-C₁₂ alkyl, -CO₂H, CO₂ substituted C₁-C₁₂ alkyl,

Z-arylene-CO₂H, Z-arylene-CO₂ alkyl, -CO₂C₁-C₁₂ alkyl

-SO₂Cl, -SO₂F, -NCO, -NCS

5

In the above list Z is selected from O, NH, N-C₁-C₁₂ alkyl, N-aryl, S, SO₂, Si or a direct bond.

When A contains the reactive group any of the above may be attached to the metal. For example:

Al
AlOarylene-CH=CH₂, **AlOC**₁-C₁₂alkylene arylene-CH=CH₂, **Al S** arylene CH=CH₂.

$$\text{C}_1\text{-C}_{12} \text{ alkyleneCH=CH}_2, \text{ Si[Oarylene CH=CH}_2\text{]}_2, \text{ Al NHC}_1\text{-C}_{12} \text{ alkylene CH=CH}_2$$

15 Si[OC₁-C₁₂ alkylene arylene CH=CH₂]₂, Si[NHC₁-C₁₂ alkylene arylene CH=CH₂]₂, and

$$\text{Si}[\text{OC}_{1-12} \text{ alkylene arylene CH=CH}_2\text{}]_2$$

5 In the above definitions the term "C₁-C₁₂ alkyl" is used to describe straight or branched chain monovalent hydrocarbon radicals containing 1-12 carbon atoms.

The term "substituted C₁-C₁₂ alkyl" is used to describe C₁-C₁₂ alkyl substituted with at least one group selected from C₁-C₁₂ alkoxy, halogen, trifluoromethyl, cyano, C₃-C₈ cycloalkyl, aryl, aryloxy, arylthio, arylsulfonyl, heteroaryl, NHCOC₁-C₁₂ alkyl, NHCO₂ C₁-C₁₂ alkyl, NHCO aryl, NH SO₂ aryl, NHCONH C₁-C₁₂ alkyl, NHCONH aryl, carbamoyl, sulfamoyl, SO₂F, CONH C₁-C₁₂ alkyl, -S heteroaryl, CONH aryl, SO₂ NH C₁-C₁₂ alkyl, SO₂ N(C₁-C₁₂ alkyl)₂, SO₂ NH aryl, CONH C₃-C₈ cycloalkyl, SO₂NH C₃-C₈ cycloalkyl, CON(C₁-C₁₂ alkyl) aryl, SO₂N(C₁-C₁₂ alkyl) aryl, COC₁-C₁₂ alkyl, CO aryl, thiocyno, S C₁-C₁₂ alkyl, S aryl, SO₂ C₁-C₁₂ alkyl, SO₂ aryl and heteroaryl.

15 The term C₁-C₁₂ alkylene is used to describe straight or branched chain divalent saturated hydrocarbon radicals and these substituted with one or more groups selected from halogen, C₁-C₁₂ alkoxy, C₃-C₈ cycloalkyl and aryl.

The term "aryl" is used to describe phenyl and naphthyl radicals and these optionally substituted with halogen, C₁-C₁₂ alkoxy, C₁-C₁₂ alkyl, trifluoromethyl, cyano, SO₂ C₁-C₁₂ alkyl, thiocyno, hydroxy, O CO C₁-C₁₂ alkyl, COC₁-C₁₂ alkyl, CO₂ C₁-C₁₂ alkyl, formyl, carbamoyl, sulfamoyl, C₃-C₈ cycloalkyl, NHCO₂ C₁-C₁₂ alkyl, CON(C₁-C₁₂ alkyl)₂, CONH C₃-C₈ cycloalkyl, SO₂NHC₃-C₈ cycloalkyl, SO₂NH phenyl, CO phenyl, CONH phenyl, NHCO C₁-C₁₂ alkyl, NHCO C₃-C₈ cycloalkyl, S heteroaryl, SO₂NH C₁-C₁₂ alkyl, CONH C₁-C₁₂ alkyl, SO₂N(C₁-C₁₂ alkyl)₂, CON(C₁-C₁₂ alkyl) phenyl, SO₂N(C₁-C₁₂ alkyl) phenyl, CON(C₁-C₁₂ alkyl) phenyl, -SO₂N(C₁-C₁₂ alkyl) phenyl, SO₂ phenyl, S phenyl, O phenyl, NHCO₂ phenyl and NHCO phenyl, wherein each phenyl may contain one or more substituents selected from C₁-C₁₂ alkoxy, halogen and C₁-C₁₂ alkyl.

The term "heteroaryl" is used to represent mono or bicyclic heteroaromatic radicals containing at least one "hetero" atom selected from oxygen, sulfur and nitrogen or a combination of these. Examples of these suitable heteroaryl groups include: thiazolyl, benzothiazolyl, pyrazolyl, pyrrolyl, thienyl, furyl, thiadiazolyl, oxadiazolyl, benzoxazolyl, benzimidazolyl, pyridyl, pyrimidinyl, and triazolyl and these radicals substituted with one or more of the substituents mentioned above for the term "aryl".

The term "halogen" is used to include fluorine, chlorine, bromine and iodine.

35 The term "polymer forming reactive group" is used to describe a variety of reactive groups useful in making polymers and which are well-known in the art. A variety of these groups are disclosed by the examples of substituents (S) described above.

Specific examples of suitable NIRFs and methods for their preparation are known in the art and described in U.S. Patents 4,255,273; 5,292,855; 5,336,714; 5,397,819;

5 5,461,136; 5,525,516; 5,553,714 and 5,423,432, which are incorporated herein by reference.

The NIRF compounds may be admixed in the binder substrate as monomers or admixed or copolymerized into the thermoplastic resins, which are admixed into the binder substrate. Alternatively the NIRFs could be admixed or copolymerized into a second
10 copolymer, which could be admixed in the binder substrate or copolymerized in the thermoplastic resin. Preferably, the NIRFs are admixed or copolymerized in the thermoplastic resins.

15 For copolymerized NIRFs the polymer backbone is any backbone, which is soluble, dispersible or emulsifiable in the binder substrate, or thermoplastic resins which are used as the main vehicle in the printing media. Suitable polymer backbones include polyesters, polyurethanes, polyolefins, polyamides, polysulfonamides, polyamines, polysiloxanes, polyacrylates, polyvinylacetates, polymethacrylates, polystyrenes,
20 polysulfides and mixtures thereof. Specific polyester backbones include, but are not limited to polyester NIRF compositions prepared from sebacid acid or dodecanedioic acid, diethylene glycol or poly(ethylene) glycols and copolymerizable NIRF dyes as described in US 5,397,819 and 5,461,136, which is incorporated herein by reference.

It will be appreciated by one skilled in the art that the reactive group S is selected
25 to be readily polymerizable to prepare a selected backbone structure via appropriate techniques of homopolymerization or copolymerization. Thus for polyester backbones, polyester reactive groups such as alkyl-OH, alkyl-CO₂-alkyl, alkyl-CO₂H, alkyl-CO₂-aryl, aryl-CO₂H, aryl-CO₂-alkyl, and the like would generally be selected. Copolymerization yields copolymerized NIRFs similar to the compounds described in US Patents 5,292,855;
30 5,336,714 and 5,423,432, which are each, incorporated herein by reference. These copolymerized polyester/thermally stable near infrared fluorophoric compounds include squaraine, phthalocyanine and naphthalocyanine type compounds, however other porphine type compounds as described above are also suitable.

Preparation of suitable backbone polymers is well known in the art and need not
35 be described in detail here.

The copolymerizable compounds of the present invention, can be readily formulated into invisible thermally meltable inks which are suitable for thermal transfer.

Generally only small amounts of the NIRFs of the present invention are required to achieve the desired result. Amounts between about 10 ppm and 1000 ppm are sufficient.

5 The thermal transfer ribbon of the present invention is produced in a two stage process wherein the first stage includes preparation of a specific wax emulsion or formulation and the second stage includes preparation of the transfer coating or layer.

Generally, a wax adhesive emulsion uses hydrocarbons, paraffin or ozokerite, carnauba, microcrystalline waxes and an ethylene vinyl acetate copolymer and/or a hydrocarbon resin soluble in aliphatic solvents. The wax emulsion uses waxes plus the acetate copolymer plus the hydrocarbon resin in one formulation. In another formulation the wax emulsion uses waxes plus the acetate copolymer of the hydrocarbon resin.

One embodiment of the present invention comprises a dispersion of an acetate copolymer, at least one acrylic resin, carbon black and at least one invisible NIRF compound. Suitable examples of the components and their amounts are well known in the art. The resulting dispersion was coated at 20-25°C onto the ribbon backing element 14 at a dry coat weight of 3 +/- 0.5 grams per square meter to form finished NIRF thermal transfer printing ribbon 10. When NIRF thermal transfer printing ribbon 10 was contacted with a sheet of paper or some other print receiving medium from the side of the printing media layer 12, using a thermal print machine or stamping tool to apply heat images to the ribbon 10 from the uncoated side of the ribbon backing element 14, a thermal transfer of the single printing media layer 12 to the paper or other print receiving medium occurred.

This produced a positive transfer image on the paper or other print receiving medium which appears black when viewed under broad spectrum light or black light. For example, if a bar code image was thermally printed using ribbon 10, the positive transfer image on white paper would appear as shown in FIG. 6 when viewed under broad spectrum light or black light. It also left a negative image on the ribbon 10. When the positive image was viewed with a near infrared ~~fluorescence~~ camera designed for display of contrast images of the near infrared fluorescence on a video monitor, a very faint image could be discerned. The weakness of the image is due to carbon black absorption of most of the activating laser light and near infrared fluorescence generated before it can exit the image surface. Use of black dye compositions, which do not absorb strongly in the near infrared in place of the carbon black pigment results in stronger contrast images.

Referring to FIG. 2, NIRF thermal transfer and printing ribbon 30 comprising a single printing media layer 32 which is adhered to one side of the ribbon backing element 34. Printing media layer 32 comprises a uniform dispersion of monomeric or polymeric NIRF dye compositions 38 in binding substrate 40 without any visible marking compounds. NIRF compositions are inactive under broad spectrum light and black light. Thus, images printed using ribbon 30 are transparent or invisible under broad spectrum

5 light and black light, but the fluorescence generated when activated with appropriate near infrared light frequencies can be detected using a suitable detector or imaging device.

When ribbon 30 was contacted with a sheet of paper or some other print receiving medium from the side of the single printing media layer 32, using a thermal printing machine or stamping tool to apply heat images to the ribbon 30 from the side of the ribbon
10 backing element 34, a transfer of the single printing media layer 32 to the paper or other print receiving medium occurred. This produced a positive transfer image on the paper or other print receiving medium which is invisible when viewed under broad spectrum light or black light. For example, if a bar code image were thermally printed using ribbon 30, the positive transfer image on white paper would be invisible when viewed under broad
15 spectrum light or black light (see FIG. 6A). However, the transfer image could be detected or decoded with a near infrared fluorescence bar code scanner. Moreover, a strong image could be discerned as depicted on FIG. 6B when the transfer image was imaged with a near infrared fluorescence camera designed for display of contrast images of the near infrared fluorescence.

20 The thermal transfer also left a negative image of the bar code on the ribbon 30, which is invisible under broad spectrum light or black light, but can be examined with a near infrared fluorescence camera which permits display of a contrast image on a video monitor as depicted on FIG. 6.

In contrast to these results, a UV thermal transfer printing ribbon prepared as
25 described in US Patent 5,516,590 (FIG. 2) was contacted with a sheet of paper from the side of the single printing media using a thermal printing machine or stamping tool to apply heat images to the ribbon from the side of the ribbon packing element to transfer the single printing media layer to paper. This produced a positive thermal transfer image on the paper, which is invisible when viewed under incandescent broad spectrum light but
30 easily discerned by human vision under black light and conventional fluorescent lighting systems.

Another embodiment of the present invention comprises an emulsion of mineral spirits, copolymer resin, thermoplastic resin, wax and at least one invisible NIRF compound. Suitable examples of the components and their amounts are well known in the
35 art.

The emulsion is coated onto ribbon backing element 34 at a dry coat weight of about 3 grams per square meter to form ribbon 30 which performed well when used to transfer images to paper as described above.

5 A fourth preferred formulation for the NTRF thermal transfer printing and marking ribbon of the present invention is given below:

Ingredient	% Dry	% Dry Range	Grams Dry	Grams Wet
Water	-----	-----	-----	70
Aqueous Polymer	22	15-30	22	22
Emulsion				
Eastman Aqueous NIRF	8	5-15	8	8
Polymer Emulsion				
(Example 2)				
	<u>30</u>	-----	<u>30</u>	<u>100</u>
Water	-----	-----	-----	70
Aqueous Polymer	22	15-30	22	22
Emulsion				
Eastman Aqueous NIRF	8	5-15	8	8
Polymer Emulsion				
(Example 10)				
	<u>30</u>	-----	<u>30</u>	<u>100</u>

In the above preferred formulation of ribbon 30, the aqueous polymer emulsion is described in US 5,552,231, Example 1, minus the carbon black pigment and the Eastman

10 Aqueous NIRF Polymer emulsions are water dissipatible, sulfomonomer containing
polyesters described in US Patent Application Docket 70278; the disclosures of which ^{are} ~~one~~
incorporated herein by reference.

To fabricate a ribbon like 30 shown in Figure 2 with the above formulation, the aqueous polymer emulsion is blended by rapid stirring at 20-25°C with the Eastman aqueous NIRF polymer emulsion according to the recipes shown. The resulting emulsions were coated at 20-25°C onto the ribbon backing element 34 at a dry coat weight of 3.1 + or - 0.5 grams per square meter to form ribbon 30 which performed well when used to transfer images to paper as described.

Referring now to FIG. 3, a third preferred embodiment of a NIRF thermal transfer printing and marking ribbon 38 in accordance with the present invention, generally indicated by reference numeral 50, is shown. Ribbon 50 consists of a first printing media layer 52 which is adhered to one side of ribbon backing element 54, and second printing media layer 62 which is adhered to the top surface of first printing media layer 52. First printing

5 media layer 52 preferably includes a uniform dispersion of a monomeric or polymeric NIRF dye composition in binding substrate 60. Second printing media layer 62 preferably includes a uniform dispersion of visible black or colored pigments 56 in binding substrate 64. Thus, images printed using ribbon 50 comprise a bottom layer of second printing media layer 62 with a uniform dispersion of black or colored pigments 56 in binding substrate 64 and a top layer of first printing media layer 52 with a uniform dispersion of monomeric or
 10 polymeric NIRF dye compositions 58 in binding substrate 60. Since the compositions 58 are transparent, and thus invisible under broad spectrum light and black light, visible black or colored pigments 56 allow the printed images to appear visibly black or colored, as desired, under broad spectrum light or black light. However, compositions 58 generate near infrared fluorescence when activated by appropriate near infrared light frequencies
 15 from lasers or LED ^(light emitting diode) sources, and this fluorescence can be detected using a suitable near infrared detector, scanner or camera.

use TH
 NK SK
 BH

red or TH use
 NK SK
 BH

20 Binding substrates 60 and 64 retain the dispersion of compositions 58 and 56 in their respective layers prior to the printing operation and once the layers are transferred onto the print receiving media. It is important that the two layers remain contiguous after the transfer so that the NIRF composition 58 in layer 52, are not mixed with the black or colored pigments 56 in layer 62 to minimize unwanted absorption of the infrared laser light by the black or colored pigments 56 in layer 62, which would reduce the efficiency of the detection by the NIRF camera (Example 2).

25 Referring now to FIG. 4 and 5, a fourth preferred embodiment of a NIRF thermal transfer printing and marking ribbon in accordance with the present invention, generally indicated by reference numeral 70, is shown.

30 Ribbon 70 consists of first spot coated printing media layer 72 which is adhered to one side of ribbon backing element 74, and second printing media layer 82 which is adhered to the surface of first spot coated printing media layer 72 distal from backing element 74 and to portions of backing element 74 not covered by first spot coated printing media layer 72.

35 First spot coated printing media layer 72 preferably includes a uniform dispersion of monomeric or polymeric NIRF dye composition 78 in binding substrate 80 spot coated in any desired pattern or configuration on ribbon backing element 74. For example, first spot coated printing media layer 72 could be spot coated in a pattern or configuration identifying a particular store's name, logo or some other desired identifiable configuration, as represented by repeating pattern 86 of ABC's shown in FIG. 5. Second printing media layer 82 preferably includes a uniform dispersion of visible black or colored pigments 76

5 in binding substrate 84. Images printed using ribbon 70 consist of a bottom layer of second printing media layer 82 with a uniform dispersion of visible black or colored pigments 76 in binding substrate 84 and a top layer of first spot coated printing media layer 72 with the spot coated pattern or configuration of uniform dispersion of NIRF dye composition 78 in binding substrate 80. Since composition 78 is transparent, and thus invisible under broad spectrum light, visible black or colored pigments 76 allow the printed images to appear
10 visibly black or colored, as desired, under broad spectrum light or black light as shown in FIG. 6. NIRF dye composition 78 present in repeating pattern 86 generate near infrared fluorescence when activated by appropriate ^{red or} near infrared light frequencies from lasers or LED sources, and this fluorescence can be detected using an appropriate detector, scanner or imaging camera designed for display of contrast images of the fluorescence or a video
15 monitor (see Example 2) for inspection as shown in FIG. 7.

Binding substrate 80 retains the spot coated uniform dispersion of NIRF dye composition 78 against backing element 74 prior to the printing operation. Similarly, binding substrate 84 retains the uniform dispersion of visible black or colored pigments 76
20 prior to the printing operation. In addition, binding substrate 80 retains the spot coated uniform dispersion of NIRF dye composition 78 and binding substrate 84 retains the uniform dispersion of visible black or colored pigments 76 after second printing media layer 82 and first spot coated printing media layer 72 are transferred onto paper or some other printing medium.

25 Referring now to Figures 8 and 9, a fifth preferred embodiment of a NIRF thermal transfer printing and marking ribbon in accordance with the present invention, generally indicated by reference numeral 90, is shown. Ribbon 90 consists of first spot coated printing media layer 92 which is adhered to one side of ribbon backing element 94, second spot coated printing media layer 102 which is adhered to the same side of ribbon
30 backing element 94, and third printing media layer 108 which is adhered to the surfaces of first spot coated printing media layer 92 and second spot coated printing media 102 distal from backing element 94 and to portions of backing element 94 not covered by first spot coated printing media layer 92 and second spot coated printing media layer 102.

First spot coated printing media layer 92 preferably includes a uniform dispersion
35 of monomeric or polymeric NIRF dye composition 98 in binding substrate 100 spot coated in any desired pattern or configuration on ribbon backing element 94. Similarly, second spot coated printing media layer 102 preferably includes a uniform dispersion of monomeric or polymeric NIRF dye composition 110 in binding substrate 104 spot coated in any desired pattern or configuration on ribbon backing element 94. For example, first

- 5 spot coated printing media layer 92 could be spot coated in a first pattern or configuration represented by repeating pattern of ABC's shown in FIG. 9, identifying, for example, a particular product brand name, and second spot coated printing media layer 102 could be spot coated in a second pattern or configuration as represented by repeating pattern 112 of XYZ's shown in FIG. 9, identifying, for example, a particular product logo or trademark.
- 10 If desired, second spot coated printing media layer 102 could be allowed to overlap first spot coated printing media layer 92 in a predetermined manner. Third printing media layer 108 preferably includes a uniform dispersion of visible black or colored pigments 96 in binding substrate 114.

- Images printed using ribbon 90 consist of a bottom layer of third printing media
 15 layer 108 with a uniform dispersion of visible black or colored pigments 96 in binding substrate 114 and a top layer of first spot coated printing media layer 92 with the spot coated pattern or configuration of uniform dispersion of monomeric or polymeric NIRF dye composition 98 in binding substrate 100 and second spot coated printing media layer 102 with the spot coated pattern or configurations of uniform dispersion of monomeric or
 20 polymeric NIRF dye composition 110 in binding substrate 104. Since 98 and 110 are transparent, and thus invisible under broad spectrum light and black light, visible black or colored pigments 96 allow the printed images to appear visibly black or colored, as desired, under broad spectrum light as shown in FIG. 10. Monomeric or polymeric NIRF dye composition 98 present in repeating pattern 106 and monomeric or polymeric NIRF
 25 dye composition 110 present in repeating pattern 112 generate near infrared fluorescence when activated by appropriate near infrared light frequencies from lasers or LED sources, and this fluorescence can be detected by a suitable detector, scanner or imaging camera. The unique pattern created by the fluorescence and imaged by a near infrared fluorescence camera is shown in FIG. 11 for the case of monomeric or polymeric NIRF dye
 30 compositions 98 and 110 being identical. If 98 and 110 are selected to be non-identical, then either 98 or 110 can be detected using the camera configuration described in Example 2 and either repeating pattern 106 or 112 will be stored in the digital camera memory and can be observed on the video monitor.

If the camera ^{filters} ~~filters~~ are reconfigured to permit detection of fluorescence generated
 35 by excitation of the printed repeating pattern 106 or 112 in FIG. 9 which previously was not recorded, by excitation with appropriate near infrared light from a laser correct for NIRF dye composition 98 or 110, then the other repeating pattern 106 or 112 will be selectively stored in the digital camera memory and can be observed on the monitor. Thus, by correct selection of laser excitation sources and filters on the camera described in

5 Example 2, it is possible to visualize the image of either repeating pattern 106 or repeating pattern 112. If desired, both images so recorded can be displayed simultaneously as shown in FIG. 11, with the luminosity of the image from repeating pattern 106 slightly different from repeating pattern 112, due to differences in the overall efficiencies of the two NIRF
10 detection processes. Selective detection of images from repeating pattern 106 or from repeating pattern 112 is an additional security feature made possible by using ribbon 90 of the present invention, which is not possible using near ultraviolet fluorescent pigments exposed to black light, instead of near infrared fluorescent dye compositions described herein.

Binding substrates 100 and 104 retain the spot coated uniform dispersions of
15 monomeric or polymeric NIRF dye composition 98 and 110 in their layers prior to the printing operation and after the printing media is transferred to the print receiving media.

The print media layer of the present invention may also include additional components to achieve certain desired results. Such additional components may include, but are not limited to molecular weight modifiers, charge modifiers, plasticizers and cross
20 linking agents.

The NIRF thermal transfer printing and marking ribbon of the present invention is superior to the ultraviolet fluorescent thermal transfer printing and marking ribbon previously disclosed in the prior art. UV fluorescent images or marks are easily activated, and visualized by human vision under black light, and even under many conventional room
25 lighting conditions such as fluorescent bulbs. This makes it easy to locate such images or marks under a black light. The images and marks of the present invention are not easily identified by human vision under black light, broad spectrum light, or infrared light. Hence the present invention provides a superior feature in security marking of ID documents and items of commerce to prevent fraudulent use, counterfeit, substitution, and
30 diversion of consumer or industrial products.

The images and marks of the present invention have superior light, thermal, and chemical stability and are more resistant to fluorescence quenching mechanisms commonly encountered in formulation of thermal transfer ribbons. Moreover, the NIRF dyes can be used at lower concentrations due to greater overall absorbance and fluorescence quantum
35 efficiencies.

Printing of ultraviolet fluorescence bar codes on paper and other print receiving media containing interference ultraviolet absorbing or fluorescing compositions (deriving from original manufacture, recycling manufacture, or contamination during manufacture or

5 prior to printing) creates serious problems in successful bar code scanning and decoding. NIRF bar code printing and scanning systems are free from interferences deriving from background near infrared fluorescence or absorption because such materials are very rarely encountered in paper or other print receiving materials, as well as in the commercial world, in general.

10 Images or marks made from the thermal transfer compositions of the present invention may be detected or imaged in a number of ways. For example, the images could be detected by a simple "yes/no" detector, which detects the presence, but not the configuration of the mark or image. Alternatively the images or marks may be detected using a scanner which can detect and distinguish unique images such as barcodes or a near
15 infrared fluorescence camera designed for display of contrast images of the fluorescence on a video monitor.

Methods for printing marks or images comprising at least one invisible NIRF compound are also disclosed. A suitable method comprises the steps of providing a thermal transfer ribbon comprising a ribbon backing element and at least one printing
20 media layer comprising at least one invisible NIRF compound; and contacting said ribbon backing element with a heating element so as to contact said printing media layer with a print receiving media under conditions sufficient to thermally transfer an image thereto.

Also disclosed in the present invention is a method comprising the steps of exciting a thermal transfer image containing at least one invisible NIRF compound with
25 radiation having a wavelength between about 630 nm and 1100nm; and detecting fluorescence emitted from said invisible NIRF compound.

Suitable NIRF cameras are designed to detect and display contrast images of the fluorescence on a video monitor for human visualization and/or inspection, as shown in Figure 7. An example of suitable instrumentation for higher power laser scanning for a digital camera is described as follows: The excitation source is a 780 nm (50 mW) laser
30 diode such as those available from Lasermix Inc., Rochester, New York coupled with a scanning system. The scanner system comprises a real-time galvanometer-based point scanning system with near uniform illumination. Scanning head and the control boards (General Scanning Inc., Watertown, Massachusetts) are powered by a triple DC power supply (VIZ model WP 708A, General Scanning Inc., Watertown, Massachusetts). The x-
35 y scan head comprises of a 8 kHz counter-rotating scanner and a moving magnet galvanometer. The galvanometer provided the vertical scan and the counter-rotating scanner provided the horizontal scan. Three control boards were supplied with the scan head: the pixel clock, counter-rotating scanner driver and a moving magnet galvanometer

5 servo-controller. The sinusoidal motion of the counter-rotating scanner was corrected by phase locking the pixel clock to the scanner and by adjusting the clock rate to match the sinusoidal velocity. The scanning system had a frame rate of up to 100 frames per second.

The detection system comprised a CCD camera (model HPC-2 large area CCD Imaging System, Spectra source Instruments, California), thermoelectrically cooled by a
10 cooling unit and controlled by an IBM PC with an interface card. A 55 mm Nikon lens with a 2.4 f stop was used for collecting the emitted light. To achieve effective cutoff of the scattered light from excitation source and stray light, two emission bandpass filters (2", rejection ratio of 10^5) with a cutoff of 820 ± 20 nm and 820 ± 10 nm were used.

Data acquisition and analysis were performed by Windows-based software
15 supplied by Spectra source. The software also provided a script language programming to automate data acquisition and to control external devices within the application program. The software had provisions for dark field and flat field corrections. A 90 MHZ Pentium computer with 32 MB RAM was used to gather data and control the CCD camera.

Although the present invention has been described above in detail, the same is by
20 way of illustration and example only and is not to be taken as a limitation on the present invention. For example, although the use of two spot coated printing media layers has been described herein, the use of three, or even more, such spot coated layers could be readily accomplished utilizing the teachings of the present invention. It is also possible to use the present invention for thermal transfer printing of encoded information such as
25 security characters, text, bar codes, and other indicia or images on transparent tape or laminating ribbons for attachment to or lamination with a wide variety of security documents; ID, permit, credit and debit cards; etc. The information can be encrypted, encoded, and printed on the tape or lamination medium, is not visible to the human eye, but can be decoded with NIRF cameras described herein, decrypted, and displayed as images
30 on video monitors for comparison to control or standard images for information authentication as described in US 5,514,860.

Although the bar code illustrated was one dimensional, printing of two dimensional bar codes is possible and even more useful in many applications of the present invention.

35 The invention further comprises any of the following features either alone, in combination or in subcombination.

The thermal transfer ribbon of the present invention wherein said printing media layer further comprises a visible marking compound.

5 The thermal transfer ribbon of the present invention further comprising a second printing media layer wherein first printing media layer comprises at least one visible marking compound and/or at least one second near infrared fluorescent compound and said second printing media layer comprises said at least one near infrared fluorescent compound.

10 The thermal transfer ribbon of the present invention further comprising a second printing media layer comprising at least one visible marking compound and/or at least one second near infrared fluorescent compound.

 The thermal transfer ribbon of the present invention wherein said first printing media layer is coated on said ribbon backing element in a specific configuration.

15 The thermal transfer ribbon of the present invention wherein said first printing media layer is coated on said ribbon backing element in a specific configuration.

 The thermal transfer ribbon of the present invention wherein said ribbon comprises at least three print media layers serially coated on said ribbon backing element.

20 The thermal transfer ribbon of the present invention wherein at least one print media layer comprises at least one visible marking compound.

 The thermal transfer ribbon of the present invention wherein at least one printing media layer is coated on in a specific configuration.

25 The thermal transfer ribbon of the present invention wherein said printing media layer comprises a dispersion of an acetate copolymer, at least one acrylic resin and said at least one invisible NIRF compound.

 The thermal transfer ribbon of the present invention wherein said printing media layer further comprises from about 5% to about 15% carbon black dispersed therein.

 The thermal transfer ribbon of the present invention wherein said printing media layer further comprises at least one visible marking compound dispersed therein.

30 The thermal-transfer ribbon of the present invention wherein two or four of the X substituents are N.

 The thermal transfer ribbon of present invention wherein said Ar groups have 1-3 fused aryl groups.

35 The thermal transfer ribbon of the present invention wherein said Ar groups are symmetrically disposed around said porphine.

 The thermal transfer ribbon of the present invention wherein said polyester backbones include, but are not limited to polyester NIRF compositions prepared from sebacid acid or dodecanedioicacid, diethylene glycol or poly(ethylene) glycols and

- 5 copolymerizable NIRF dyes; or from terephthalic acid, 1,4-butanediol, and copolymerizable NIRF dyes.







The thermal transfer ribbon of the present invention wherein said printing media layer comprises an emulsion comprising mineral spirits, copolymer resin, thermoplastic resin, wax and between about 0.001% and about 1% of at least one invisible near infrared
10 fluorescent compound.

The ribbon of the present invention wherein said printing media layer comprises a solution of $(C_6H_5O)_4PcAlOC_6H_3-3,5-di-CO_{18}CH_3-n$ in carnauba wax and stearyl alcohol.

The thermal transfer ribbon of the present invention, wherein:
said coating layer comprises about 15 to about 30% of aqueous polymer composition
15 comprising poly(ethylene oxide) resin, casein, high density polyethylene, carnauba wax and from about 5 to about 15% of at least one water dissipatable polymer emulsion comprising at least one sulfomonomer and at least one near infrared fluorescent compound copolymerized therein.

The thermal transfer ribbon of the present invention wherein:
20 said aqueous polymer composition is present in an amount between about 20 and about 25 % and said water dissipatable polymer emulsion is present in an amount between about 5% and about 10%.

The thermal transfer ribbon of the present invention wherein said porphine is selected from the group consisting of
25



- 5 Wherein each Ar is the same or different and is independently selected from the group consisting of fused aryl ring systems having one to four aryl rings fused therein.

The thermal transfer ribbon of the present invention wherein A is selected from Zn(II), Mg (II), Sn(IV) and Ga(III) attached to a polymer reactive group selected from the group consisting of

- 10 $\text{AlOaryl}-\text{CH}=\text{CH}_2$, $\text{AlOC}_1\text{-C}_{12}\text{alkylene arylene}-\text{CH}=\text{CH}_2$, $\text{Al S arylene CH}=\text{CH}_2$

$\text{C}_1\text{-C}_{12}\text{ alkyleneCH}=\text{CH}_2$, $\text{Si[Oaryl}-\text{CH}=\text{CH}_2]_2$ $\text{Al NHC}_1\text{-C}_{12}\text{ alkylene CH}=\text{CH}_2$.


$\text{Si[OC}_1\text{-C}_{12}\text{ alkylene arylene CH}=\text{CH}_2]_2$, $\text{Si [NHC}_1\text{-C}_{12}\text{ alkylene arylene CH}=\text{CH}_2]_2$ and

15

$\text{Si[OC}_1\text{-C}_{12}\text{ alkylene arylene CH}=\text{CH}_2]_2$.

The thermal transfer ribbon of the present invention wherein said near infrared fluorescent compound is selected from phthalocyanine and naphthalocyanine of the

- 20 formulae:




wherein M is selected from the group consisting of Al O arylene $(\text{CO}_2\text{ alkyl})_2$ and $\text{Si(Oaryl}-\text{CO}_2, \text{alkyl})_2$

25

wherein S is selected from the group consisting of H, alkyl, O alkyl, O arylene $(\text{CO}_2\text{ alkyl})$ and S arylene $(\text{CO}_2\text{ alkyl})$ n is 1 or 2; and said alkyl the same or different and is selected from $\text{C}_4\text{-C}_{18}$ straight or branched alkyl and wherein said phthalocyanine has at least two alkyl groups selected from the group consisting of $\text{C}_{12}\text{-C}_{18}$ straight or branched alkyls; and

30



wherein M is selected from the group consisting of Al O arylene
(CO₂ alkyl)₂ and Si (O arylene CO₂ alkyl)₂,

wherein S is selected from the group consisting of H, alkyl, O

alkyl, O arylene (CO₂ alkyl), S arylene (CO₂ alkyl), NH

arylene (CO₂ alkyl) and NH alkylene CO₂ alkyl; and

n is 1-6; and said alkyl the same or different and is selected from
C₄-C₁₈ straight or branched alkyl and wherein said
naphthalocyanine has at least two alkyl groups selected from the
group consisting of C₁₂-C₁₈ straight or branched alkyls.

The thermal transfer ribbon of the present invention wherein said binding
substrate comprises at least one binder selected from the group consisting of caruba wax,
paraffin wax, candelilla wax, palm wax, beeswax, rice bran wax, gum arabic, poly(α-
methyl styrene), epoxy resins, acrylic resins polyethylene oxide, polytetrafluoroethylene
wax, polyurethanes, polyethylene waxes, methyl methacrylate resins, styrene-ethylene-
butylene block copolymers, ethylene vinyl acetate, ethylene methyl acrylate copolymers,
styrene butadiene elastomers, polyketones, amorphous polyester resins, cellulose esters,
polyvinyl alcohol, solid fatty acids, amides, 1-octadecanol, sebacic acid, stearamide,
behenyl alcohol, stearyl stearamide, casein, high density polyethylene emulsion, caruba

- 5 wax emulsion, glycerine, castor oil and mixtures thereof and optionally at least one additional component selected from the group consisting of plasticizers, defoamers and curing agents.

Therefore, the scope and content of the present invention are to be defined only by the terms of the appended claims.

10

EXAMPLES

Example No. 1

Components I-IV were added to a 500 mL round bottom flask, which was fitted with a vacuum outlet, stirrer, condensate take off and nitrogen inlet:

- 15 I. 78.44 (0.39 mole) sebacic acid
 II. 117.68 g (0.59 mole) poly(ethylene glycol) (Mn200)
 III. 75 ppm Ti catalyst as Titanium (IV) butoxide
 IV. 0.14 g (1.25×10^{-4} mole) infrared fluorescent compound
 $[(C_6H_5O)_4PcAlOC_6H_3-3,5-di-CO_2CH_3]$
 20 Pc =phthalocyanine nucleus - compound of Example 4 of U.S.
 Patent 5,336,714

The flask and contents were immersed in a Belmont metal bath at 200°C with a nitrogen sweep over the reaction mixture and held for 1.0 hr. The temperature was increased to 220°C, held for 2.0 hours, and then increased to 270°C over about 10 minutes.

- 25 Vacuum was then applied to lower the pressure to about 0.1 torr over about 30 minutes and the polycondensation reaction completed by heating at about 270°C for 30 minutes. The resulting polymer which contains about 1000 ppm of copolymerized near infrared fluorophore has an inherent viscosity of 0.49 as measured in a 60/40 ratio by weight of phenol/tetrachloroethane at a concentration of 0.5g per 100 mL. By gel permeation
 30 chromatography, the polymer, which was a very viscous liquid, has a weight average molecular weight (M_w) of 21,190, a number average molecular weight (M_n) of 8182, and a polydispersity ($M_w \div M_n$) value of 2.68. The procedure was repeated using 0.28 g dye and .42 g dye to give analogous polymers having 2000 ppm and 3000 ppm copolymerized NIRF dye and respective IVs (M_w ; M_n ; $M_w \div M_n$) as follows: .48 (21,000; 8050; 2.61)
 35 and .49 (21,300; 8250; 2.58).

5 Example No. 2

A coating composition consisting of a mixture of 5g UCAR Latex emulsion 379 (Union Carbide) and 5 g Eastman aqueous NIRF polymer emulsion described in US Application Docket No. 70278, Example 9 except using 0.2 g NIRF compound of Example 29 of US Patent 5,397,819 instead of 0.4 g was coated on white paper to give a thin
10 uniform film approximately 1-2 mils thick after drying. The dry coating had about 10 ppm of NIRF dye polymer. The coating was marked with crossing line patterns using a black ink pen to give a contrast image (Test Paper 1). Using the thermal transfer printing ribbon of the present invention it is possible to transfer bar code patterns to white paper which are invisible (Test Paper 2). The Test Paper 1 was excited in a dark room with a 670 nm. one
15 milliwatt laser source by manual and rapid continuous scanning of the laser beam over the crossing line patterns. The scanning was continued while a modified Kodak digital camera system was permitted to record any light received from the target pattern during a pre-selected exposure time. The digital camera system (DCS) used a Nikon F-3 camera body with standard 35 mm SLR accessories (5.8 inches wide x 5.8 inches high x 3.8 inches
20 deep-weight about 3.5 pounds less lens system). The DCS had a E-O back with a high resolution charge couple device (CCD) 1280 x 1024 pixel array (16 micron square pixels, equivalent ASA of up to 1600, 2.5 images per second in a burst, using Nikon F-3 lens and accessories). The camera was mounted on a vertical holding device which permitted positioning a static object horizontally underneath the camera lens to permit focusing. The
25 light (i.e. electronic signal) recorded by exposure of Test Papers at a distance of about 10 inches from the camera lens was stored in a digital storage unit designed to receive the electronic signals generated by the E-O (electro-optical) CCD sensor which converts photon or light energy to an electronic signal. The DCS digital storage unit was 4 (four) inches high x 10.25 inches wide x 13.25 inches deep (weight about 11 pounds including
30 battery pack for remote operation). The specifications are: with rechargeable battery pack (standard camcorder type), 12 MHZ 80C188 processor, 8MB image DRAM (32M Byte optional), 200 M Byte Winchester hard disk (store up to 156 images). Optional JPEG compression (stores up to 600 images), user selectable equivalent ISO of 200, 400, 800, or 1600 (with B& W unit), 12 button membrane keyboard, SCSI parallel interface, optional
35 RS-232 serial interface, NTSC video interface (RS-170) for external video monitor or processing, 2 line x 16 character backlit LCD alphanumeric display, preview images on built in 4 inch LCD display. The Kodak megapixel array M-3 was used in the camera. The 35 mm lens was removed and a 710 nm band pass filter was mounted on top of the 35

5 mm lens (between the lens and CCD to ensure that only fluorescence light photons reach the CCD) and the modified lens re-installed.

In total darkness, a four second exposure of a control coating containing no NIRF polymer was made using 670 nm laser scanning activation (as described above) provided by a 670 nm 1 milliwatt laser pen modified with a 670 nm. band pass filter which reduced the power approximately 50% to about 0.5 milliwatt. No image was recorded or displayed on the 4 inch LCD preview display and only a black screen was displayed on the external still record to a XL-7700 thermographic printer on Kodak electronic print paper. The image 2339 control (4 second with 710 filter) was black. When the experiment was repeated by manual scanning 4 seconds the crossing line patterns drawn on top of the fluorophore containing coating (Test Paper 1), image 2336 was detected in total darkness and a bright contrast image was recorded. It was obvious that where the manual scanning dwell time was longest, the white signal was strongest. A similar result was obtained with coatings containing 20 ppm and 1.8 ppm NIRF polymer using ½ second exposure, (Images 2268 and 2293). It was obvious from the signal intensities that much lower concentrations would be feasible (parts per billion and possibly parts per trillion). Images of large diameter circle patterns and checker – board patterns were recorded and printed (Images 2341 and 2334). Coatings prepared using a NIRF polymer requiring 780 nm. activation produced no images using the 670 nm. laser activation thereby demonstrating the selectivity possible with this imaging technique. The test coatings prepared using the 1.8 ppm 670 NIRF polymer and the 10 ppm 780 NIR polymer were invisible when viewed under broad spectrum light or black light. Since the electronic image information recorded can be stored, amplified, computer enhanced, decrypted if necessary with appropriate software for required mathematical algorithms of encryption, and transmitted at the speed of light over large distances, this imaging system is suitable for many identification, authentication, surveillance, tracing, and marking applications. Test Paper 2 when imaged with a digital imaging camera produces sharp well defined positive bar code images which, if encrypted as a 2D bar code, can be decoded using appropriate computer software to display the decrypted printed information on the video monitor or print it on a XL-7700 thermographic printer using Kodak electronic print paper. The feasibility of identification over larger distances using a higher power laser scanning activation system and the digital camera further modified with more powerful near infrared light accumulating lens accessories was demonstrated using NIRF polymer coatings on small 2D and 3D targets placed at distances from a few feet to 100 feet. An example of suitable instrumentation for

5 higher power laser scanning for a digital camera is described as follows and shown in FIG. 12:

The excitation source is a 780 nm (50 mW) laser diode such as those available from Rochester, New York coupled with a scanning system. The scanner system comprises a real-time galvanometer-based point scanning system with near uniform
10 illumination. Scanning head and the control boards (General Scanning Inc., Watertown, Massachusetts) are powered by a triple DC power supply (VIZ model WP 708A, General Scanning Inc., Watertown, Massachusetts). The x-y scan head comprises a 8 kHz counter-rotating scanner and a moving magnet galvanometer. The galvanometer provided the vertical scan and the counter-rotating scanner provided the horizontal scan. Three control
15 boards were supplied with the scan head: the pixel clock, counter-rotating scanner driver and a moving magnet galvanometer servo-controller. The sinusoidal motion of the counter-rotating scanner was corrected by phase locking the pixel clock to the scanner and by adjusting the clock rate to match the sinusoidal velocity. The scanning system had a frame rate of up to 100 frames per second.

20 The detection system comprised a CCD camera (model HPC-2 large area CCD Imaging System, Spectra source Instruments, California), thermoelectrically cooled by a cooling unit and controlled by an IBM PC with an interface card. A 55 mm Nikon lens with a 2.4 f stop was used for collecting the emitted light. To achieve effective cutoff of the scattered light from excitation source and stray light, two emission bandpass filters (2",
25 rejection ratio of 10^5) with a cutoff of 820 ± 20 nm and 820 ± 10 nm were used.

Data acquisition and analysis were performed by Windows-based software supplied by Spectra source. The software also provided a script language programming to automate data acquisition and to control external devices within the application program. The software had provisions for dark field and flat field corrections. A 90 MHZ Pentium
30 computer with 32 MB RAM was used to gather data and control the CCD camera.

Less sensitive and expensive CD imaging detectors were designed and constructed to permit continuous observation on a video monitor of the near infrared fluorescence produced by activation of invisible bar codes or other information printed using the NIRF thermal transfer printing and marking ribbons of the present invention. In these devices,
35 appropriately selected cut on filters were chosen to detect (pass) the fluorescence light and reject the laser excitation light received from test samples examined at a pre-set distance alternatively side by side versus standard or control samples in a small black viewing box (about 3 inch x 6 inch x 12 inch) designed to eliminate background light interference from

5 any source. This device permits authentication of the printed invisible markings or visualization of other printed information.

In one embodiment of an inexpensive portable fluorescence imaging device, a Marshall Electronics (Culver City, CA) Model V-1055 CCD camera (12V DC 100 ma, 0.005 lux 510-492 pixels, 3 ounces, 1 ½"x1 ½"x1" with a Marshall Electronics V-4508, 8 mm, f 1.3 lens was mounted inside the top surface of a 12" tall, 6" long and 3" wide plastic box, which was open at the bottom. On one side of the camera a 3 mW, approximately 675 nm diode laser (Power Technology Inc., Little Rock, AR, Model PM03(670-5)) was mounted. The laser's lens was defocused to produce an illuminated area of approximately 1" x 3" at the open bottom of the box. On the other side of the camera an approximately 10mW, 780 nm Laser was mounted. This laser's lens was also defocused to illuminate an area of about 1" x 3" at the bottom of the box. The camera and lasers were connected to a battery pack holding eight AA batteries. All eight batteries in series were used to power the 780nm laser and the camera. Only three of the batteries were needed for the 675 nm laser. By connecting one or the other of the lasers to the battery pack, the fluorescence from items marked with fluorophores requiring excitation near 780 nm or near 675 nm could be induced when the imaging device was placed onto such items. To image the fluorescence from the marked items, an appropriate filter was placed in front of the camera's lens using a plastic holder. When using the 675 nm laser, bandpass filters centered at either 720 nm or 730 nm (Corion Holliston, MA, models 510-720-F or 510-730-F, bandpass of 12 nm FWHM) or long-pass cut-on filters with a cut-on wavelength of 715 nm or 725 nm (Oriel Instruments, Stratford, CT, Catalog #51345 or 51315) were used. The cut-on filters are best used in pairs of two stacked back-to-back. For use with the 780 nm laser, band pass filters centered at 820 nm, 830 nm or 840 nm (Corion, 510-820-F, 510-830-F or 510-840-F) or Schott Glass equivalent RG-830 or RG 850 Long pass, cut-on filters (Oriel Instruments, Catalog #51352 or 51360, also used in pairs) are placed in front of the camera. The images can be viewed on a handheld 2.7" diagonal video monitor (Sony FM 030 watch CAM) that is connected to the camera. Alternatively for better image quality, the camera could be connected to any standard television monitor.

In an even more compact imaging device, the model V-1055 (Marshall Electronics) with a V-4508 lens was mounted inside a plastic housing 7.5" tall x 3" wide x 4" long. The camera was mounted in such a way as to place the front of the lens 3 ¼" above an 2 ¼" x 1 ¼" opening. Four 5 mW, 780 nm Laser diodes without collimating lenses were placed 2" from the opening and spaced so as to relatively evenly illuminate any object placed under the opening in the box. Each laser diode was powered by a laser

5 diode driver. A 3" diagonal or active matrix color LCD monitor (Sony Model XV-M30) was mounted on a swivel to the top of the plastic housing. All power was supplied by a 12V lead-acid camcorder battery. Two RG-850 long-pass optical filters were used in front of the camera lens to reject the laser light, but pass the fluorescent light.

10 Example No. 3

Components I-IV were added to a 500mL round bottom flask, which was fitted with a Dean-Stark trap and a reflux condenser:

- I. Yellow Carnauba T1 Wax (62 g.) or Rice Bran Wax (71 g.)
- II. Stearyl alcohol (2.1g.)
- 15 III. 75 ppm Ti catalyst as titanium (IV) butoxide
- IV. .02 g NIRF dye (C₆H₅O)₄ PcAlOC₆H₃-3,5-di-CO₂CH₃- compound of Example 4 of US Patent 5,336,714.

The mixture was heated 18 min. at 202°C and then at 164°C with stirring for 2 hours; during this time the dye gradually was converted to the stearyl ester derivative and
20 methanol distilled into the Dean Stark trap (plus trace quantities of nBuOH). As the reaction progressed the dye dispersed well into the wax solvent. At the end of the reaction (judged complete by TLC and FDMS analysis of a sample of the reaction mixture) the product was used directly in preparing NIRF thermal transfer printing and marking ribbon 30 shown in FIG. 2 as described above.

25

Example No. 4

The procedure of Example No. 3 was repeated using .02 g NIRF dye (tert-butyl)₄ NcAlOC₆H₃-3,5-di-CO₂CH₃ in place of component IV. At the end of the reaction the product (tert-butyl)₄ NcAl OC₆H₃-3,5-di-CO₂C₁₈H_{37-n} dispersion in Carnauba wax or Rice
30 Bran Wax and stearyl alcohol was used directly in preparing thermal transfer printing and marking ribbon type 30 shown in FIG. 2 as described above.

Example No. 5


The procedure of Example No. 3 was repeated using .02 g NIRF dye (tert-Butyl)₄
35 NcSi (OC₆H₃-4-CO₂CH₃)₂ in place of component IV. At the end of the reaction the product (tert Butyl)₄ NcSi(OC₆H₃-4-CO₂C₁₈H_{37-n})₂ dispersion in Carnauba wax or Rice Bran Wax and stearyl alcohol was used directly in preparing thermal transfer printing and marking ribbon type 30 shown in FIG. 2 as described above.

5 Example No. 6

The procedure of Example No. 3 was repeated using .02 g NIRF dye (C_6H_5S)₄ $PcAlOC_6H_3-3,5-di-CO_2CH_3$ in place of component IV. At the end of the reaction the product (C_6H_5S)₄ $PcAlOC_6H_3-3,5-di-CO_2C_{18}H_{37}$ -n dispersion in Carnauba wax or Rice Bran Wax and stearyl alcohol was used directly in preparing thermal transfer printing and marking ribbon type 30 shown in FIG. 2 as described above.

10 Example No. 7

The procedure of Example No. 3 was repeated using .02 g NIRF dye shown below for which $R=CH_2CH_2CH_2CH_2CH_3$ in place of component IV and 4 g of stearyl alcohol. At the end of the reaction the product $R=(CH_2)_{17}CH_3$ dispersion in Carnauba wax or Rice Bran Wax and stearyl alcohol was used directly in preparing thermal transfer printing and marking ribbon type 30 shown in FIG. 2 as described above.

20 Example No. 8

5 g of the mineral spirits formulation given for ribbon 30 shown in FIG. 2 described above is mixed with 2 g. of a solution of 30 mg. of tetra-phenyl-naphthalocyanine aluminum hydroxide dissolved in 100 g. methylene chloride solution. The mixture is stirred well and then coated on the ribbon backing element 34 shown in

5 **FIG. 2.** The ribbon 30 so prepared is used to print invisible images of a dinosaur on white paper by using a hot rubber stamp on the back side of ribbon 34 (temperature of the stamp at 120-160°C, mild hand applied pressure for 5 seconds at each temperature). When the ribbon 30 so used was peeled off the white paper, a positive dinosaur image could be
10 viewed on a video monitor when the invisible positive image on the paper was detected with the near infrared fluorescence cameras described in Example 2 above, or when the negative image on ribbon 30 was detected with these cameras.

5 Example No. 9

Example 8 is repeated with the same image results using 5 g of a solution prepared from 5 g polymer X-25251-137 containing 2000 ppm aluminum phthalocyanine chloride and 1.064 g tetra-butyl ammonium bromide dissolved in 130 g methylene chloride. This solution required 2 days to prepare and contained a fine precipitate of sodium bromide which was very difficult to filter and therefore not removed.

Polymer X-25251-137 was prepared as follows by adding components I-VII to a 500 mL round bottom flask which was fitted with a vacuum outlet, stirrer, condensate take off and nitrogen inlet:

- I. 81.74g dimethyl isophthalate
- 15 II. 27.35g 5-sodiosulfo -1,3-isophthalic acid
- III. 44.15g diethylene glycol
- IV. 34.07g 1,4-cyclohexane dimethanol
- V. .74g sodium acetate
- VI. .28g chloroaluminum phthalocyanine
- 20 VII. 75 ppm Ti catalyst as Titanium (IV)butoxide


The flask and contents were immersed in a Belmont metal bath at 200°C with a nitrogen sweep over the reaction mixture and stirred well for 1.0 hour. The temperature was increased to 220°C, held for 2.0 hours, and then increased to 250°C over about ten minutes; vacuum was then applied to lower the pressure to about 0.1 torr about 36 minutes and the polycondensation reaction completed by heating at about 250°C for 25 minutes. The polymer produced which contains copolymerized near infrared fluorophore has an inherent viscosity of .337 as measured in a 60/40 ratio by weight of phenol/tetrachloroethane at a concentration of 0.5g per 100 mL. The glass transition temperature (Tg) was 51°C.

5


We claim:

1. A thermal transfer ribbon comprising:
a ribbon backing element and at least one printing media layer comprising
at least one near infrared fluorescent compound in a concentration which
provides detectable fluorescence without imparting color to a mark made
from said printing media layer.
2. A method for applying a mark comprising at least one invisible near infrared
fluorescent compound said method comprising the steps of providing a thermal
transfer ribbon comprising a ribbon backing element having coated on one side at least
one printing media layer comprising at least one invisible NIRF compound; and
contacting the non-coated side of said ribbon backing element with a heating element
so as to contact said printing media layer with a print receiving media under conditions
sufficient to thermally transfer an image to said print receiving media.
3. A method for detecting a thermal transfer mark comprising at least one invisible NIRF
compound wherein said method comprises the steps of exciting said at least one
invisible NIRF compound having a peak absorbance with radiation within 50
nm of said peak absorbance; and detecting fluorescence emitted from said invisible
NIRF compound.
4. The method of claim 3 wherein said exciting step is effected by a laser or LED.
5. The method of claim 3 wherein said detecting step is effected by a device selected
from the group consisting of near infrared non-imaging detectors, scanners and
imaging cameras.
6. The thermal transfer ribbon of claim 1 or 2 wherein said at least one invisible near
infrared fluorescent compound is selected from monomeric and copolymerized dye
compositions.
7. The thermal transfer ribbon of Claim 3 wherein said near infrared fluorescent
compound is at least one porphine compound of the formula:



35



wherein each X may be the same or different and is selected from nitrogen and carbon substituted with Y, wherein Y is selected from hydrogen, C₁-C₁₂ alkyl, substituted C₁-C₁₂ alkyl, C₃-C₈ cycloalkyl, aryl and heteroaryl, m is 1 through 9; R₁ - R₈ are the same or different and are selected from hydrogen, C₁-C₁₂ alkyl, substituted C₁-C₁₂ alkyl, C₃-C₈ cycloalkyl, aryl and heteroaryl and wherein adjacent R₁-R₈ groups may represent the following parts of aromatic and heteroaromatic ring systems:



wherein A is selected from 2(H) atoms bonded to diagonally opposite nitrogen atoms, Zn(II), Mg(II), Al (III) bonded to halogen, oxygen, sulfur or nitrogen, Sn IV atoms bonded to halogen, oxygen, sulfur or nitrogen, Si IV bonded to halogen, oxygen, sulfur or nitrogen and Ga III bonded to halogen, oxygen, sulfur or nitrogen; and S may be the same or different and is a metal which produces near infrared fluorescence selected from Li, Na, K, Be, Mg, Ca, Sc, Y, La, Ac, Ti, Zr, Hf, Cr, Mo, W, Mn, Tc, Re, Fe, Ru, Os, Co, Rh, Ir, Ni,

- 5 Pd, Pt, Cu, Ag, Au, Zn, Cd, Hg, In, Tl, Ge, Pb, As, Sb; lanthanides selected from Pr, Nd, Sm, Eu, Gd, Dy, Ho, Er, Tm, Yb, Lu; and actinides selected from Th, Pa, U, Np.
8. The thermal transfer ribbon of Claim 7 wherein at least one S substituent further comprises a polymer forming reactive group which is substituted into Y, at least one R_1 - R_8 group or a mixture thereof.
- 10 9. The thermal transfer ribbon of Claim 7 wherein S is selected from the group consisting of:
- O-arylene $\text{CH}=\text{CH}_2$, O- C_1 - C_{12} alkylene arylene- $\text{CH}=\text{CH}_2$, O- $\text{CH}_2\text{CH}=\text{CH}_2$,
O- C_1 - C_{12} alkylene- $\text{CO}_2\text{CH}=\text{CH}_2$, O- C_1 - C_{12} alkylene- $\text{CO}_2\text{C}(\text{CH}_3)=\text{CH}_2$, OC- C_1 - C_{12} alkylene $\text{OC}(\text{CH}_3)=\text{CH}_2$,
 C_1 - C_{12} alkylenearylene- $\text{CH}=\text{CH}_2$, NH-arylene- C_1 - C_{12} alkylene- $\text{CO}_2\text{CH}=\text{CH}_2$, $\text{OCC}(\text{CH}_3)\text{C}_1$ - C_{12} alkyl,
 $\text{NHCCH}(\text{O})=\text{CH}_2$, C_1 - C_{12} alkylene-NHCCH(=O)= CH_2 , NH arylene NHCOCH=CH₂,
Z- C_1 - C_{12} alkylene-I, Z-arylene-CHO, Z- $\text{CH}_2\text{CH}(\text{O})\text{CH}_2$, Z-arylene $\text{CH}(\text{O})\text{CH}_2$,
-NH₂, Z-arylene-NH₂, Z- C_1 - C_{12} alkylene-NH₂, $\text{OCC}(\text{CH}_3)=\text{CH}_2$, $\text{OCC}(\text{O})\text{CH}=\text{CH}_2$, $\text{CH}_2\text{CH}(\text{O})\text{CH}_2$,
Z-arylene- CO_2 - C_1 - C_{12} alkylene-I, CO_2 - C_1 - C_{12} alkylene-I, NHC_1 - C_{12} alkyl,
Z-arylene- $\text{SO}_2\text{CH}=\text{CH}_2$, C_1 - C_{12} alkylene- $\text{SO}_2\text{CH}=\text{CH}_2$, C_1 - C_{12} alkylene-Z- $\text{CH}(\text{O})\text{CH}_2$,
 , Z-arylene-NH- , $\text{OCC}(\text{O})\text{C}_1$ - C_{12} alkyl,
- $\text{SO}_2\text{CH}=\text{CH}_2$, Z- C_1 - C_{12} alkylene- $\text{SO}_2\text{CH}=\text{CH}_2$, Z-arylene-Z- $\text{CH}_2\text{CH}(\text{O})\text{CH}_2$,
Z- C_1 - C_{12} alkylene-OH, Z- C_1 - C_{12} alkylene-O-C(=O)- C_1 - C_{12} alkyl, OH, C_1 - C_{12} alkylene-OH,
 C_1 - C_{12} alkylene- CO_2H , C_1 - C_{12} alkylene- CO_2 - C_1 - C_{12} alkyl, - CO_2H , CO_2 substituted C_1 - C_{12} alkyl,
Z-arylene- CO_2H , Z-arylene- CO_2 alkyl, - CO_2C_1 - C_{12} alkyl
- SO_2Cl , - SO_2F , -NCO, -NCS

- 15 wherein Z is selected from the group consisting of O, NH, N- C_1 - C_{12} alkyl, N-aryl, S, SO_2 , Si and a direct bond.

5

10. The thermal transfer ribbon of claim 7 wherein said near infrared fluorescent compound is copolymerized into a polymer backbone selected from the group consisting of polyesters, polyurethanes, polyolefins, polyamides, polysulfonamides, polyamines, polysiloxanes, polyacrylates, polyvinylacetates, polymethacrylates, polystyrenes, polysulfides and mixtures thereof.

10




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 6A



Fig. 6B




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12

INTERNATIONAL SEARCH REPORT

Inter. Application No
PCT/US 97/03556

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B41M3/14 B41M5/38 G06K7/12 B42D15/10 G07D7/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 B41M G06K G07D B42D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 157 568 A (IMPERIAL CHEMICAL INDUSTRIES PLC) 9 October 1985 see page 2, line 25 - page 4, line 9; claims 1-9; examples 1-66 ---	1,2,6,7
X	EP 0 420 613 A (TOYO INK MANUFACTURING COMPANY LIMITED) 3 April 1991 see page 3, line 30 - line 53 see page 4, line 27 - page 5, line 13 see page 5, line 49 - line 58 see claims 1-14; examples 1-9 ---	1-7
A	WO 89 00319 A (GLOBAL SECURITY AKTIEBOLAG) 12 January 1989 see page 2, line 16 - page 4, line 30 see claims 1,2,8; figures 1,2 --- -/--	1-10

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed

- * "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- * "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- * "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * "&" document member of the same patent family

Date of the actual completion of the international search

30 May 1997

Date of mailing of the international search report

23. 06. 97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Bacon, A

A. S. Bacon

INTERNATIONAL SEARCH REPORT

Intern. Application No.
PCT/US 97/03556

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 81 03507 A (GAO GESELLSCHAFT FÜR AUTOMATION UND ORGANISATION MBH) 10 December 1981 see page 1, line 4 - line 10 see page 4, line 6 - line 27 see page 5, line 10 - line 28 see claims 1-34; example 1 ---	1-10
P,X	EP 0 719 654 A (HITACHI MAXELL LIMITED) 3 July 1996 see page 2, line 5 - line 10 see page 3, line 6 - line 37 see claims 1-10; figures 1-7; examples 1-7 see page 5, line 40 - page 6, line 4 -----	1-7

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 97/03556

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 157568 A	09-10-85	JP 7096339 B JP 60224589 A US 4788128 A	18-10-95 08-11-85 29-11-88
EP 420613 A	03-04-91	JP 3111462 A JP 7086179 B JP 2507819 B JP 3180384 A DE 69029888 D DE 69029888 T US 5348348 A	13-05-91 20-09-95 19-06-96 06-08-91 20-03-97 22-05-97 20-09-94
WO 8900319 A	12-01-89	SE 461359 B AU 1967988 A SE 8702710 A	05-02-90 30-01-89 31-12-88
WO 8103507 A	10-12-81	CH 659098 A DE 3121491 A EP 0052624 A FR 2484334 A GB 2088919 A,B SE 455710 B SE 8107667 A US 4452843 A	31-12-86 13-05-82 02-06-82 18-12-81 16-06-82 01-08-88 21-12-81 05-06-84
EP 719654 A	03-07-96	JP 8183952 A JP 8310108 A	16-07-96 26-11-96